

DESIGN MIX / MANHOLE WALL CONCRETE LINER

Ideal Ready Mix Co., Inc.

1969 IA-92 W

Oskaloosa, IA 52577

Phone: (641) 673-7756

Seven Bag Portland (4,500 PSI @ 28 Days)

3/4" Crushed Stone Aggregate

Propex Fibermesh synthetic fiber reinforcing (*see attached*)

Xypex Crystalline Waterproofing (*see attached*)

3% Air Entrainment

5" Slump

References:

Cement: ASTM C150, Type II

Hydrated Lime: C207, Type S

Fine Aggregate: ASTM C33

Course Aggregate: ASTM C33 (with maximum aggregate size of 3/4 inch)

Water: Potable